

KDRS ACOL



Radiata Pine RACOL is specially selected kiln dried and graded for recover of longer length clear furniture or molding components. It is random width (RW) with boards up to 400mm wide so is highly suited to selective linear ripping then cross cutting into longest length clear parts. It is ideal for molding, picture frame and furniture manufacturers.

Kiln drying is done using medium temperature schedules, to a moisture content range of 8~12%. All boards are graded from the worst face into A, B or C grades, C grade is restricted to max 5% with balance being B & better. FSC chain of Custody is available.

Boards are tallied using random width stick tally with volume of each board marked on face, some wane is allowed but if in excess it is scaled off on volume of board.

A boards must have minimum 30% 100x 1220 or 125 x 1050mm clear cuttings

B boards must have minimum 25% 100 x 700mm clear cuttings

C boards must have minimum 25% 50 x 450mm clear cuttings

No blue stain allowed, no pith, no holes.

Pencil wane only is allowed on one edge

No coloured birds eye and needle fleck.

Boards must be straight with minimal bow and crook.

Condition: Kiln dried, untreated, rough sawn

Sizes: Thickness: 25,38,40,45,50 55mm. Widths: random width 100mm and wider, average width 200mm

Packaged: Packed to width, thickness and length, grades mixed in packet

