

LumberLink[®]

新西兰良柏木材有限公司

22 x 90 utility grade profiled H3 treated decking



Product Description: Treated New Zealand Radiata Pine Utility Grade allows partially intergrown knots, max 55mm, on face along with pockets. Face is Merch type grade. No wane, no pith but may have occasional loose knot.

Back is merch grade with larger partially intergrown knots and occasional loose knots. Larger partially occluded knots may be on the back face along with open pockets.

Boards are an ideal cross cut grade to extract shorter length higher quality decking boards. All boards end stamped to certify treatment standard.

Decking must be fixed with correct nails or screws with minimum length of twice thickness of board. 22mm thickness must be used with maximum 400~450 mm joist spacing.

Treatment Chemicals: CCA pressure treatment is full penetration right through boards. All treatment is to NZS MP3640:1992 and NZTPC timber preservation quality assurances processes. CCA provides protection against fungal decay and wood boring insects. Preservatives are fixed into the wood cell structure for minimal leaching.

Treatment level: H3- Moderate decay hazard, above ground, full exterior uses such as decks, garden furniture and fencing

Specifications: Profiled with ribbed pattern on best face and smooth surface on back face. Dried, profiled, pressure treated then packaged as WAT (wet after treating). Highly suitable for cross cutting to short length appearance quality knotty decking boards.

Profiled size 22 x 90mm
Lengths 2.7 m and longer, very heavy to 4.8m
Grade Utility

Lumberlink Limited, P.O. Box 76357, Manukau City, Auckland, New Zealand

E-mail: sales@lumberlink.co.nz

Tel +64 9 263 5946

Fax +64 9 263 5924